

02-70-0086**MVQ –Silicone Rubber Standard****Description**

- This is a vinyl methyl silicone rubber (MVQ)

Property

- Vulcanisations of silicone have a resistance to cold up to approx. -60 °C
- Low temperature flexibility is not due to the addition of special plasticizers but is an intrinsic property of the polymer
- Excellent resistance to ozone, aging and weather
- Excellent electrical isolator
- Not resistant against aromatic mineral oils, fuels, silicone oil and greases

Typical applications

- Suitable for food use
- Physiologically safe
- Resistant to X-rays
- Hot gases

Further information

- Please test the suitability of the material by means of the list of chemical resistances

Conformity

- ADI-free
- REACH-compliant
- RoHS-compliant



Technical specifications			
			[Value]
Color			red or translucent
Specific gravity	DIN 53479	[g/cm ³]	1.25
Hardness	DIN 53519	[Shore A]	70 ±5
Tensile strength	DIN 53504	[MPa]	4 - 10
Elongation at tear	DIN 53504	[%]	100 - 600
Compression set	DIN 53517		
During 22h and +100 °C	25% compression	[%]	20 - 50
Temperature			[°C] -60 - +200

Note: The information displayed is correct, complete and up to date to the best of our knowledge and belief. Kubo Tech AG cannot be held liable for the accuracy or completeness of the contents. No warranty or assurance is given with respect to product features or capabilities. No legal rights are derived from the contents of this data sheet.